



TECHNICAL DATA SHEET

# KEIM MINERAL MASONRY PAINT

## FOR BRICK, MASONRY, AND STUCCO

### 1. PRODUCT DESCRIPTION

Mineral Masonry Paint is a ready-to-use, mineral sol-silicate matte flat paint for exterior masonry, concrete, and stucco surfaces. The penetrating formula forms permanent chemical bonds within the brick and masonry surface, so it will never peel or lose adhesion. It provides extremely low maintenance and a durable water-repellent finish. This paint is highly vapor permeable, allowing brick and masonry to breathe naturally. Mineral Masonry Paint will never blister or bubble due to moisture vapor in the surface. Both the binder and pigment are completely UV-resistant and lightfast, ensuring that the paint colors will not fade for decades.

- Lightfast – will not fade
- All components are completely UV-stable
- Excellent weathering resistance
- Resistance to industrial pollutants and acid rain
- Highly water-repellent
- Extremely vapor permeable
- Resistant to fungal and algae growth
- No solvents – extremely low VOC
- Easy application
- Very durable, even in extreme freeze-thaw environments

### 2. FIELD OF APPLICATION

Mineral Masonry Paint is a 2- or 3-coat system formulated for exterior use on new or bare mineral surfaces, as well as previously painted ones. It is ideally suited to masonry, brick, and stone, as well as aged concrete substrates, CMU, cement boards, plasters, and Portland stucco. It is ideal for historic restoration, maintenance, and new construction in most climates. It is not suitable for use over previously painted surfaces of elastomeric, oil-based paints or lacquers and varnishes. DO NOT use on floors.

### 3. PRODUCT PROPERTIES

KEIM Mineral Masonry Paint boasts a proven track record of exceptional longevity. The mineral silicate emulsion binder provides excellent weather resistance and color retention. Colors are non-yellowing and won't fade, regardless of the intensity of UV exposure. It is also impervious to acid rain and other environmental pollutants.

- Non-film-forming, won't ever peel
- Mineral matte finish — very natural appearance
- Non-flammable – will not burn
- Anti-static – surfaces stay clean longer

### Technical data

Specific Weight	approx. 1.45 g/cm <sup>2</sup>
pH Value @ 20°C	11
Wind Driven Rain ASTM E 514	Passes—no water leaked through
Water Vapor Permeability ASTM E 96	77 perms
Accelerated Weathering Test ASTM G 154	Passes No change after 2016 hours
Mildew Resistance ASTM D3273/D3274	Passes
Gloss at 85°	0.5 Mineral Dead Flat
Flashpoint	Non-Flammable
Color Stability Color code acc. To BFS Tech. No 26	A1 Best in class rating No color change after 4 years
VOC	<1g/liter
All test results performed on 2 coats Mineral Masonry Paint applied at 300—350 SF/GAL and 14-day cure @ 77°F & 50% RH	

### Color Shades and Textures

White and full color range. Custom color matches are also available.

## TECHNICAL DATA SHEET – KEIM MINERAL MASONRY PAINT

Mineral Masonry Paint is also available as a texture base to fill in minor cracks, pits, and voids and to provide a uniform texture on rough surfaces. MMP Texture Base MUST be finished with a final coat of Mineral Masonry Paint and not left to weather without a topcoat.

### Environmental Compliance

EPA	YES
LEED	YES
CARB	YES
SCAQMD	YES
EPD	YES
UL Greenguard Gold	YES
Cradle to Cradle Certification	YES

### 4. SPECIFICATIONS/SYSTEMS

For proper waterproofing and weather resistant performance, 2 coats of Mineral Masonry Paint must be applied at recommended coverage rates. Surface should be fully coated, with no pinholes, runs, voids or holidays.

#### Brick Masonry (new or aged, bare)

1 coat MMP (diluted up to 10%)

1 coat MMP (undiluted)

#### Cast or Pre-cast Bare Concrete

Pretreat: Keim Heavy Duty Cleaner

Concentrate (for new concrete)

1 coat MMP (diluted up to 10%)

1 coat MMP (undiluted)

#### CMU Block

For new, extremely porous block:

1 coat CONTACT-PLUS GROB Block Filler

1 coat MMP (undiluted)

#### Stucco (new or aged, bare)

Pretreat: Keim Lime Remover (for new stucco only)

1 coat MMP (diluted up to 10%)

1 coat MMP (undiluted)

#### Previously Acrylic Painted Surfaces

1 coat MMP (diluted up to 10%)

1 coat MMP (undiluted)

Do not apply to aged, oil-based, epoxy, or urethane coatings.

### 5. SURFACE PREPARATION

**WARNING!** Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at 1-800- 424-LEAD (in US) or contact your local health authority.

The substrate must be sound, dry, absorbent, clean and free from dust and grease. Loose areas, dirt, oily substances, release agents, curing compounds, moss and algae must be completely removed.

Existing film-forming paint coatings, which are loose or poorly bonded must be removed with paint stripper or by mechanical means.

#### Highly absorbent, sanding surfaces:

Pretreat by saturating surface with KEIM Fixativ, mixed with 3 parts water, and allow to dry and cure for 12 hours.

#### New Portland Stucco:

Sinter layers on new Portland stucco or stucco repairs should be pretreated with KEIM Lime Remover, rinsed with copious amounts of clean water, and allowed to dry.

#### New Concrete Surfaces:

Remove all release, form or curing oil residues with KEIM Heavy Duty Cleaner Concentrate, rinse and allow to dry. In some cases, abrasive water blasting may be necessary to remove sealers, release compounds, and to provide an anchor pattern. Concrete and mortar must be cured at least 7 days at 75°F. Use a primer coat of Contact Plus Bonding Primer on new concrete. Aged, clean, strong and sound concrete requires no pre-treatment or primer.

Provide appropriate protection for surfaces that are not to be coated (e.g., glass, natural

**TECHNICAL DATA SHEET – KEIM MINERAL MASONRY PAINT**

stone, ceramics, etc.). Any splashes on surrounding surfaces or traffic areas must be rinsed off immediately with plenty of water.

**6. APPLICATION**

Mineral Masonry Paint may be applied by brush, roller or airless spray.

- Brush - Use a natural bristle or nylon/polyester brush
- Roller - Use a ½" to ¾" nap synthetic roller cover
- Airless Spray
  - Pressure: 3000 psi
  - Tip Size: .029--.031 in
  - Remove filters from spray gun and pump manifold

First coat

Mineral Masonry Paint may be diluted up to 10% with KEIM Mineral Dilution depending on the absorbency of the surface. Thinning is not required. Allow it to dry 12 hours or overnight before recoating. DO NOT THIN WITH WATER.

Topcoat

Apply Mineral Masonry Paint undiluted. There is no recoat window after the first coat has dried.

NOTE: For extreme weather conditions it is recommended to apply a three-coat system to ensure extra build and durability.

Application conditions

Ambient and substrate temperatures: 40°F and rising, with a minimum of below 86°F. Do not apply to sun-heated substrates. Protect coated surfaces from wind and rain for a minimum of 12 hours during and after application.

Drying times

Drying times are temperature, humidity and coverage dependent.

	@ 40-50°F	@ 50°F +
Touch:	4--6 hour	2--4 hours
Recoat:	24--48 hours	24 hours

Coverage\*

SUBSTRATE	COVERAGE*
Masonry or Brick	200—250 SF/GAL
Natural Stone Masonry	225—275 SF/GAL
Cast or Pre-Cast Concrete	275—325 SF/GAL
Fiber Cement Siding	275—325 SF/GAL

Portland Stucco	150—200 SF/GAL
CMU Block (smooth)	100—150 SF/GAL
CMU Block (split faced or fluted)	50—100 SF/GAL
*Stated values are based on our experience on smooth surfaces. Surface texture, porosity, application conditions and type of equipment used will all vary consumption. Only a test application, using desired mixing ratio and under production conditions will forecast consumption of the system components accurately. <b>NOTE: Subtract 50-75 SF from stated values for MMP Texture Base Coat.</b>	

Cleaning

Clean spills, splatters, hands, and tools immediately after use with soap and warm water. After cleaning, flush the spray equipment with a compliant cleanup solvent to prevent rusting. Tools should be kept in the paint material or in water during work breaks.

Mixing with other products

Do not mix with other products or additives and never thin with water.

**7. PACKAGING**

1-Gallon and 4-Gallon

**8. STORAGE**

Approx. 12 months in a tightly closed container under cool, frost-free conditions. Protect from heat and direct sunlight.

**9. DISPOSAL**

Dispose of completely emptied containers in accordance with local, state and federal waste regulations.

HAZARDOUS SUBSTANCE CLASS

n/a

**10. LIMITATIONS**

KEIM Mineral Masonry Paint is a façade paint finish and should not be used on floors, roofs or decks or where water will collect. Not for use below grade where hydrostatic pressure is present.

**11. SAFETY INSTRUCTIONS**

## TECHNICAL DATA SHEET – KEIM MINERAL MASONRY PAINT

Never pour contents into drains, waterways, or the ground. The Mineral Masonry paint is alkaline. Avoid contact with eyes. In the event of eye contact, flush immediately with plenty of water and consult a physician. Wear suitable gloves. Do not swallow. If swallowed, seek medical attention immediately and show this label. Wash hands thoroughly after handling it.

KEEP OUT OF REACH OF CHILDREN  
PROTECT FROM FREEZING

The stated values and properties are the result of extensive development work and practical experience. Our recommendations for application, whether given verbally or in writing, are intended to provide assistance in the selection of our products and do not establish a contractual relationship. In particular, they do not release those purchasing and applying our products from the duty of establishing for themselves, with due care, the suitability of our products for the intended application. Standard building industry practices must be complied with. We retain the right to make modifications to improve the products or their application. This edition supersedes all earlier editions.

The information and recommendations set forth in this Technical Data Sheet are based upon tests conducted by or on behalf of KEIM Mineral Coatings. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult <http://www.keim-usa.com/Technical-Data-Sheets> for the latest in product technical information.

